



ZELL WAX
INDUSTRIAL ADDITIVES

PE WAXES PRODUCT TABLE 2016

GRADE	TYPE	VISCOSITY BROOKFIELD (C.P.S.)	DROP POINT ASTM 566 (°C)	CONGEALING POINT ASTM D938 (°C)	PENETRATION 25°C ASTM D1321 (°C)	ACIDITY DIN53402 (mg KOH)	DENSITY (G/CC)	COLOUR	PRESENTATION	INDUSTRIES OF APPLICATION
CWN-105	NON OXIDIZED	15-45	105-112	95-102	6-8	0	0,95	WHITE	POWDER	
CWN-201	NON OXIDIZED	45-80	108-113	98-103	2-4	0	0,95	WHITE	POWDER	
CWN-209	NON OXIDIZED	50-80	114-120	104-110	1-2	0	0,95	WHITE	POWDER	
CWF-101	FISCHER-TROPSCH	15-35	114-118	104-108	1-3	0	0,95	WHITE	POWDER	
CWF-102	FISCHER-TROPSCH	15-30	112-115	101-105	1-3	0	0,95	WHITE	POWDER	
CWO-308	OXIDIZED PE WAX	<20	99-112	88-102	3-5	6-8	0,95	WHITE	POWDER	
CWO-312	OXIDIZED PE WAX	<20	99-112	88-102	8-10	10-15	0,95	WHITE	POWDER	
CWO-314	OXIDIZED PE WAX	<20	99-112	88-102	8-10	18-20	0,95	WHITE	POWDER	
CWO-315	OXIDIZED PE WAX	<20	99-112	88-102	8-10	20-22	0,95	WHITE	POWDER	
LUBRIZELL 160	PARAFFIN LUBRICANT	6-10	76-80	67-72	NA	0	0,95	WHITE	POWDER	

HOTMELT	POWDER PAINTS	PVC	RUBBER
ROAD MARKING	COATINGS	MASTERBATCH	CANDLES
CABLE	INKS	CITRIC EMULSIONS	TEXTILE EMULSIONS



www.zellwax.com

technical@zellwax.com Telf.: 0034 96 186 21 20 Fax: 0034 96 185 5743 Av. General Urrutia, 75. Oficinas 1-A y 3-A | 46013 | Valencia | España